

AMENDED CLAIMS WITH MARKINGS

1. (twice amended) A long life gas engine oil comprising a major amount of an oil of lubricating viscosity and a minor amount of additives comprising phenolic anti oxidants, a low ash gas engine oil detergent system having a TBN of about 50 to about 300, and viscosity index improver, but which does not contain aminic anti oxidant, wherein the oil of lubricating viscosity has a viscosity of between about 9 to [20] 13 cSt at 100°C, said oil of lubricating viscosity being a synthetic, hydrocracked or solvent refined oil or mixtures thereof, [and] wherein the phenolic anti oxidant is present in an amount in the range of about 0.1 to 2 vol% and the viscosity index improver is present in an amount in the range of about 0.1 to 3 vol% and wherein the gas engine oil has a low ash content.

Please cancel claim 2.

4. (twice amended) The long life gas engine oil of claim [2] 10 wherein the phenolic anti oxidant is present in an amount in the range of about 0.3 to 1.75 vol% and the viscosity index improver is present in an amount in the range of about 0.2 to 2 vol%.

6. (twice amended) A method for enhancing the life of gas engine oils as evidenced by a reduction in viscosity increase, oxidation, nitration, TAN increase, and TBN depletion, comprising adding to a gas engine oil base stock having a viscosity at 100°C of from 9 to [20] 13 cSt, the base stock being a synthetic, hydrocracked or solvent refined oil or mixture thereof, a minor amount of an anti oxidant in the range of about 0.1 to 2 vol% and a minor amount of a viscosity index improver in the range of about 0.1 to 3 vol%, wherein the anti

AMENDED CLAIMS WITH MARKINGS (continued)

oxidant is selected from the [groups] group consisting of phenolic anti oxidants and a minor amount of a low ash gas engine oil detergent system having a TBN of about 50 to about 300 wherein the gas engine oil has a low ash content.

Please cancel claim 7.

9. (twice amended) The method of claim [7] 12 wherein the phenol anti oxidant is added to the lubricating oil in an amount in the range of about 0.3 to 1.75 vol% and the viscosity index improver is added to the lubricating oil in an amount in the range of about 0.2 to 2 vol%.

Please add new claims 10-13.

*R 1.126*  
<sup>11</sup>  
~~10~~. The oil of claim 1 wherein the oil of lubricating viscosity is a mixture of a hydrocracked oil and a solvent refined oil.

<sup>12</sup>  
~~11~~. The oil of claim 4 wherein the detergent system is a mixture of detergent comprising at least one first alkali or alkaline earth metal salt having a TBN below about 250 and at least one second alkali or alkaline earth metal salt having a TBN of about one-half or less of the first salt.

<sup>13</sup>  
~~12~~. The method of claim 6 wherein the basestock is a mixture of a hydrocracked oil and a solvent refined oil.

<sup>14</sup>  
~~13~~. The method of claim 9 wherein the detergent system is a mixture of detergents comprising at least one first alkali or alkaline earth metal salt having a TBN below about 250 and at least one second alkali or alkaline earth metal salt having a TBN of about one-half or less of the first salt.--